



SGS United Kingdom Ltd.
Consumer Products Division

Gaw House
Alperton Lane
Alperton
Wembley
HAO 1WU
Tel: 0181 998 2171
Fax: 0181 997 9723

CHEMCO INTERNATIONAL LTD
UNITS 3a-3b EAST SHAWHEAD IND EST.
COATBRIDGE NORTH LANARKSHIRE
SCOTLAND

Attn: B DELVIN

Report No. CP 43037/DJM/98

Date : 26 May 1998

Page 1/1

Your Ref. : BD/FS/2690

SAMPLE DESCRIPTION: Vinyl Ester Tank Lining Coated Onto Metal.
Two 600micron and Two 1200micron pieces.

TEST REQUIRED: Effect of aviation fuel, (70/30 iso-octane/toluene)
for storage for 28 days at 20°C.

DATE RECEIVED: 15 April 1998.

DATE REPORTED: 26 May 1998.

METHOD: Samples cleaned with solvent, and sealed in flasks
with 100ml fuel mixture, 2 test and 2 blank.
Stored at 20°C for 28 days. Samples removed, solvent
evaporated under nitrogen. Residue determined
gravimetrically. Samples examined visually after
drying and again after a further 7 days at 20°C.

RESULTS: Residue in solvent, mg/100ml.

600micron	1200micron	Blank600	Blank1200
2.3	2.1	<0.1	<0.1

Visual assessment.

28 days. No colour change, softening, blistering,
peeling, cracking, crazing or loss of adhesion.
35 days. No change in any of the above.

REPORTED BY... *D.M. Washbrook* ...
D.M. Washbrook.
Section Head Analytical Chemistry.

AUTHORISED BY... *D.J. Martin* ...
D.J. Martin.
Analytical Chemist.